

Clinical complications in fixed prosthodontics

Charles J. Goodacre, DDS, MSD,^a Guillermo Bernal, DDS, MSD,^b Kitichai Rungcharassaeng, DDS, MS,^c and Joseph Y. K. Kan, DDS, MS^d

School of Dentistry, Loma Linda University, Loma Linda, Calif.

The purpose of this article is to identify the incidence of complications and the most common complications associated with single crowns, fixed partial dentures, all-ceramic crowns, resin-bonded prostheses, and posts and cores. A Medline and an extensive hand search were performed on English-language publications covering the last 50 years. The searches focused on publications that contained clinical data regarding success/failure/complications. Within each type of prosthesis, raw data were combined from multiple studies and mean values calculated to determine what trends were noted in the studies. The lowest incidence of clinical complications was associated with all-ceramic crowns (8%). Posts and cores (10%) and conventional single crowns (11%) had comparable clinical complications incidences. Resin-bonded prostheses (26%) and conventional fixed partial dentures (27%) were found to have comparable clinical complications incidences. The 3 most common complications encountered with all-ceramic crowns were crown fracture (7%), loss of retention (2%), and need for endodontic treatment (1%). The 3 most common complications associated with posts and cores were post loosening (5%), root fracture (3%), and caries (2%). With single crowns, the 3 most common complications were need for endodontic treatment (3%), porcelain veneer fracture (3%), and loss of retention (2%). When fixed partial denture studies were reviewed, the 3 most commonly reported complications were caries (18% of abutments), need for endodontic treatment (11% of abutments), and loss of retention (7% of prostheses). The 3 most common complications associated with resin-bonded prostheses were prosthesis debonding (21%), tooth discoloration (18%), and caries (7%). (J Prosthet Dent 2003;90:31-41.)

A complication has been defined¹ as “a secondary disease or condition developing in the course of a primary disease or condition.” Although complications may be an indication that clinical failure has occurred, this is not typically the case. It is also possible that complications may reflect substandard care. But once again, this is usually not true. Most of the time, complications are conditions that occur during or after appropriately performed fixed prosthodontic treatment procedures.

Knowledge regarding the clinical complications that can occur in fixed prosthodontics enhances the clinician’s ability to complete a thorough diagnosis, develop the most appropriate treatment plan, communicate realistic expectations to patients, and plan the time intervals needed for post-treatment care. Although a plethora of articles present clinical complications data, none provide a comprehensive comparison of the complications associated with the most commonly used restorations/prostheses.

One of the purposes of this article is to present data regarding the incidence of clinical complications associated with the following restorations/prostheses: single crowns (all-metal, metal ceramic, resin veneered metal); fixed partial dentures (all-metal, metal ceramic, resin-veneered metal); all-ceramic crowns; resin-bonded prostheses; and posts and cores. A second purpose is to identify the most common complications associated with each of these restorations/prostheses. A third purpose is to compare the restorations/prostheses on the basis of the incidence of complications encountered.

METHODOLOGY

A Medline search was initiated related to success, failure, complications, and clinical studies associated with single crowns, fixed partial dentures, all-ceramic crowns, resin bonded prostheses, and posts and cores. Reviewing the list of articles identified through the Medline search revealed additional publications, as did extensive hand searching. The literature search covered the last 50 years and focused on publications that contained clinical data regarding success, failure, and complications.²⁻¹⁶³ To be included in the calculated mean data of this report, publications must have presented clinical data that identified the number of restorations/prostheses being evaluated, how long they had been in place, and how many were affected by complications. Publications were grouped according to each type of restoration/prosthesis. The raw data from all the studies of a particular restoration/prosthesis were combined and a mean complications

^aProfessor and Dean, Loma Linda University.

^bAssociate Professor and Director, Advanced Education Program in Prosthodontics.

^cAssociate Professor, Department of Restorative Dentistry.

^dAssociate Professor, Department of Restorative Dentistry.

Presented at the Greater New York Academy of Prosthodontics annual meeting in New York, NY on December 1, 2000. Presented at the Academy of Prosthodontics meeting in Santa Fe, NM on May 21, 2001. Presented at the Annual Session of the American College of Prosthodontists, Orlando, Fla., November 7, 2002.

incidence was calculated for each type of restoration/prosthesis. The mean values were compared for the purpose of identifying which restorations/prostheses were associated with the greatest number of complications.

The most common complications associated with each type of restoration/prosthesis were identified, and a mean incidence was also calculated for each type of complication. For a specific complication to be included in this article, 3 or more studies must have reported data related to the incidence of that particular complication. Certain complications were reported in a large number of studies whereas others may have only been presented in 3 studies. Therefore the mean percentages present in this article suggest trends rather than absolute incidence values.

SINGLE CROWNS

Eight studies²⁻⁹ were included in the complications incidence data associated with single crowns. The types of crowns included all-metal, metal ceramic, and resin-veneered metal designs. One of the studies² identified the total number of complications that occurred but did not describe the nature of the complications, for example, caries and loss of retention. The other 7 studies³⁻⁹ identified both the total number of complications and the type of complications. A total of 1476 crowns were evaluated in the 8 studies, and a total of 157 were associated with some type of complication, resulting in a mean complications incidence of 11%. The length of the studies ranged from 1 year to 23 years, with an average length of about 6 years. There were additional studies¹⁰⁻¹⁸ containing complications data associated with single crowns. One of these studies¹⁸ only provided data regarding 1 type of complication (need for endodontic treatment), and it was included in the calculations related to the need for endodontic treatment. The other studies¹⁰⁻¹⁷ did not present the data in a manner that permitted the required types of calculations to be made. Therefore, they were not included in this publication.

Five of the 8 studies^{2,4,6,8,9} included in the complications incidence calculations evaluated the crowns for time periods between 1 and 4 years, and a mean complications incidence of 16% was reported. Three other studies^{3,5,7} reported data from observation times in excess of 5 years, and they reported a mean complications incidence of 7%.

Data regarding the following 5 types of complications were reported in 3 or more of the studies: need for endodontic treatment, porcelain fracture, loss of retention, periodontal disease, and caries (Table I). Two studies^{4,7} provided data about all 5 of the complications, 1 study⁶ evaluated 4 of the 5 complications, 3 studies^{3,8,9} presented information about 3 of the 5 complications, and 1 study¹⁸ provided incidence data related to only 1 complication. One other complication (tooth

Table I. Most common single crown complications

	Number crowns studied/affected	Mean incidence
Need for endodontic treatment	823/27	3%
Porcelain fracture	199/6	3%
Loss of retention	1,061/19	2%
Periodontal disease	986/6	0.6%
Caries	1,105/4	0.4%

fracture) was evaluated, but incidence data were only reported in 2 studies, and therefore the inclusion criteria were not satisfied.

Need for endodontic treatment

Five studies^{3,4,6,7,18} reported on the incidence of endodontic treatment needed in conjunction with single crowns. Of the 823 crowns studied, 27 needed endodontic treatment. There was a mean incidence of 3% and a range of 0% to 6%. The 6% incidence (3 of 51 crowns) was associated with pinledge crowns.³ Two of the 3 teeth needing endodontic treatment occurred in conjunction with tooth preparation and 1 subsequent to restoration.³

Porcelain fracture

Three studies^{4,6,9} identified the incidence of porcelain fracture with a mean rate of 3% (6 of 199 crowns studied) and a range of 2.7% to 6%.

Loss of retention

There were 5 studies^{3,4,6-8} reporting loss of retention of single crowns, with 19 crowns loosening among the 1061 crowns studied. The mean loss of retention was 2%, with a range from 1% to 23%. The highest loss of retention (23%) was associated with pinledge restorations evaluated for a mean time of 98 months and an observation time range from 75 to 108 months. Twelve of the 51 pinledges loosened over this time period.

Periodontal disease

Five studies^{3,6-9} evaluated the periodontal health around single crowns, reporting a mean complication incidence of 0.6% (6 of 986 crowns affected). One study³ reported only small differences in the periodontal results between restored teeth and controls. Only 1 crown produced a significant difference in the plaque index, gingival index, and pocket depth.³ Another study⁶ reported a lower percentage of gingivitis around the crowns after 2 years when compared to baseline conditions. Bergman et al⁸ noted only minor periodontal changes after 2 years, and Nilson et al⁹ found the periodontal health around single crowns to be comparable to the control teeth after 26 to 30 months.

Table II. Most common fixed partial denture complications

Need for endodontic treatment	Number of prostheses or abutments studied/affected	Mean incidence
Caries	3360/602 abutments 1354/113 prostheses	18% of abutments 8% of prostheses
Need for endodontic treatment	2514/276 abutments 1357/88 prostheses	11% of abutments 7% of prostheses
Loss of retention	1906/137 prostheses	7%
Esthetics	1024/58 prostheses	6%
Periodontal disease	1440/62 prostheses	4%
Tooth fracture	1602/44 prostheses	3%
Prosthesis fracture	1192/24 prostheses	2%
Porcelain veneer fracture	768/17 prostheses	2%

Caries

Four of 1105 crowns evaluated in 6 studies^{3,4,6-9} developed carious lesions, producing a mean incidence of 0.4% with a range from 0% to 2.7%.

FIXED PARTIAL DENTURES

The incidence of complications associated with fixed partial dentures was determined by evaluating data from 19 clinical studies.^{2,5,13,19-34} The types of fixed partial dentures included all-metal, metal ceramic, and resin veneered metal prostheses but did not include resin bonded prostheses. A total of 3272 fixed partial dentures were evaluated in the 19 studies, and a total of 866 prostheses were associated with some type of complication, producing a mean complications incidence of 27%. The length of the 19 studies ranged from 1 year to 20 years, with an average length of about 8 years. There were other studies^{16,17,36-44} containing data that were not included in this publication. One article³⁶ presented information about fixed partial dentures by calculating survival rates with the Kaplan-Meier method. Two other articles^{37,38} performed meta-analyses of available studies and provided survival data. Additional publications^{16,17,39-44} contained fixed partial denture clinical data, but they were not published in a form that permitted inclusion in this article.

Six of the included studies^{2,13,19,20,27,28} evaluated the fixed partial dentures for periods between 1 and 4 years, reporting a mean complications incidence of 20% (148 of 737 prostheses affected). One study¹³ did not provide a mean study length. The prostheses were evaluated over periods of 1 to 11 years, and a decision was made to include this study¹³ in the 1- to 4-year group. Nine studies^{21-26,29,30,32} evaluated the prostheses for periods between 5 and 14 years, and a mean incidence of 27% (555/2046 prostheses) was calculated for this group. One of the studies²² in this group had a mean length of 4.9 years, and a decision was made to include the data in the 5- to 14-year group. In 4 studies,^{5,31,33,34} the pros-

theses were examined after 15 to 20 years, and the mean complications incidence for this group was 27%.

Data regarding the following 8 complications were reported in multiple studies and therefore were included in this paper: caries, need for endodontic treatment, loss of retention, periodontal disease, esthetics, tooth fracture, prosthesis fracture, and esthetic veneer fracture (Table II). One study³³ evaluated all 8 complications. Three of the studies^{23,25,31} evaluated 7 of the 8 complications, 4 studies^{5,32,34,35} reported on 6 of the 8 complications, 3 studies^{20,22,27} provided data on 5 of the 8 complications, 6 studies^{26,28-30,45,46} limited their reporting to 2 to 3 complications, and 2 studies^{18,47} only reported on 1 complication. Four of the studies^{2,13,19,21} included in this article identified the number of prostheses that failed but did not provide data regarding the cause of the failure or information about complications.

There were other complications evaluated (in addition to the 8 reported in this article), but they were not reported in a sufficient number of publications to be included in this study. These factors included pain and sensitivity, mobility, edentulous ridge mucosa, root resorption, temporomandibular joint problems, possible reaction to metal, phonetic problems, and marginal fit.

Caries

Fifteen studies evaluated the incidence of caries, but in 2 different ways. Some studies^{22-24,26-28,35,45,46} presented the caries incidence in relation to the number of abutments affected and determined that 602 of 3360 abutments became carious for a mean incidence of 18% and a range from 0% to 27%.

Other studies^{5,20,22,23,25-27,31-33} evaluated caries according to the number of prostheses affected and determined that 8% of the prostheses were affected (113 of 1354 prostheses). The caries incidence ranged from 0.7% to 26%. Four studies^{22,23,26,27} presented the data as it related to both abutments and prostheses.

Need for endodontic treatment

The endodontic incidence was also presented both according to the number of abutments and number of prostheses affected. Eleven studies^{5,18,22,24,26,27,35,44-47} related the incidence of endodontic treatment to the number of abutment teeth, and the mean abutment incidence was 11% (276 of 2514 abutments affected). The range was from 3% to 38%.

Eight studies^{22-25,27,33-34} related the incidence to the number of prostheses affected, thereby providing a prosthesis incidence. Of the 1357 prostheses evaluated, 88 required treatment for a mean incidence of 7% and a range of 0.7% to 21%.

Loss of retention

Fourteen studies^{5,20,22-25,27-29,31-34,46} evaluated the loss of retention of fixed partial dentures. In the 14 studies, 137 of 1906 prostheses loosened for a mean incidence of 7% and a range from 0.0% to 13%.

Esthetics

An unsatisfactory esthetic result was found in 58 of 1024 prostheses evaluated in 7 studies.^{5,22,23,25,31,33,34} There was a mean esthetics complications incidence of 6% and a range from 2% to 12%.

Periodontal disease

Thirteen studies^{5,20,22,23,25,26,30-35,45} assessed the periodontal health around prostheses. Of the 1440 prostheses evaluated, 62 adversely affected periodontal health. There was a mean incidence of 4% and a range from 0% to 17%.

Tooth fracture

The incidence of abutment tooth fracture was recorded in 14 studies.^{5,20,22,23,25-34} The data were provided in relation to the number of prostheses in which fracture occurred. There was not a sufficient number of studies reporting the number of abutments that fractured to include the data in this article. The mean prosthesis incidence was 3% (44 of 1602 prostheses recorded abutment tooth fracture). The range was from 0.7% of prostheses to 25% of prostheses.

Prosthesis fracture

Eight studies^{5,20,23,25,32-35} assessed the incidence of framework fracture with 24 prostheses fracturing from a combined study group of 1192 prostheses. The mean incidence was 2%, with a range from 0.7% to 4%. The studies in which framework fractures occurred involved mostly long span prostheses, and many of the prostheses had cantilevered pontics (single and double cantilevers).

Table III. Most common all-ceramic crown complications

	Number of crowns studied/affected	Mean incidence
Fracture	4277/318	7%
Loss of retention	545/11	2%
Pulpal health	1088/15	1%
Caries	1650/13	0.8%
Periodontal disease	942/0	0.0%
(no significant changes)		

Porcelain veneer fracture

Five studies^{25,27,31,33,35} provided data about veneer fractures, with 17 of 768 prostheses affected by fracture. The mean incidence was 2%, with a range from 0.6% to 4%.

ALL-CERAMIC CROWNS

Complications encountered with all-ceramic crowns are presented in 22 clinical studies.^{4,48-69} A total of 4277 crowns were evaluated, and 357 exhibited some type of complication, producing a mean complications incidence of 8%. In the 22 studies, the observation times were as short as 1 month and as long as 14 years. The average length was about 4 years. Other studies reported data about all-ceramic crowns but were not included in this publication for 2 reasons. Three studies⁷⁰⁻⁷² presented complications data that were subsequently published after longer time periods, and therefore these 3 studies were excluded in favor of the longer studies. Other publications^{10,13,16,17} did not provide data in formats that permitted inclusion.

Eighteen of the included studies^{4,49-61,63,65,68,69} evaluated the crowns for periods between 1 and 4 years and recorded a mean complications incidence of 7% (range of 0% to 18%). Four studies^{48,62,64,66} were 5 or more years in length and reported a mean complications rate of 14% (range of 8% to 18%).

The 22 clinical studies provided data regarding the following 5 complications: crown fracture, loss of retention, need for endodontic treatment, caries, and periodontal disease (Table III). One study⁶⁴ provided data regarding all 5 of the reported complications. Five of the studies^{55,57-59,63} presented data regarding 4 of the 5 complications, and 5 articles^{53,60-62,68} provided information about 3 of the 5 complications. There were 5 studies^{4,48,51,65,69} that identified data for 2 of the complications, and 6 publications^{49,50,52,54,56,66} only reported data about 1 complication (crown fracture). Other factors were evaluated in the studies but not in the required number of studies, and therefore no data are included in this report. The factors included inadequate form/color,⁶³ marginal fit/smoothness,⁶³ marginal discoloration,⁶³ tooth sensitivity,^{56,57} and occlusal evenness.⁶³

Crown fracture

All 22 clinical studies^{4,48-69} provided data regarding crown fracture. A total of 318 of the 4277 crowns fractured for a mean incidence of 7% and a range from 0% to 16%. The fracture incidence varied with the length of the study. There were 18 studies^{4,49-61,63,65,66,69} of 1 to 4 years in length, reporting a mean fracture incidence of 5% and a range of 0% to 16%. Four studies^{48,62,64,66} evaluated the crowns after 5 years or more and reported a mean fracture incidence of 13% (192 of 1,520 crowns) and a range from 5% to 14%.

Fracture was evaluated as it related to crown position in the arch and wear facets/occlusal habits. Data regarding these 2 factors were reported in a sufficient number of studies to be included. The effect of 5 other factors (age,⁶⁶ gender,^{66,68} etching/type of cement,⁶⁶ finish line form,⁶⁷ and ceramic thickness⁶⁷) on crown fracture was evaluated, but only in 1 or 2 studies. The data were therefore not included in this article.

The relationship between fracture and the location of the crown (anterior, premolar, molar) was evaluated in 10 studies.^{56,59,62,67-70,72-74} The mean fracture rates for anterior (40 of 1255 crowns fractured), premolar (46 of 712 crowns fractured), and molar crowns (138 of 670 crowns fractured) were 3%, 7%, and 21%, respectively.

Four studies^{49,56,59,68} assessed the effect of occlusal habits and the presence of wear facets in the mouth. Three of these studies^{56,59,68} indicated these characteristics were not substantively correlated with crown fracture, whereas 1 study⁵⁰ indicated there was a critical relationship.

Loss of retention

Four studies^{58,59,64,65} indicated the number of crowns that came loose during the study. There was a mean loss of retention of 2% (11 of 545 crowns loosened), with a range from 0.3% to 5%.

Need for endodontic treatment

Twelve studies^{4,51,55,57-65} identified the number of restored teeth needing endodontic treatment. Of the 1088 all-ceramic crowns evaluated, 15 teeth needed treatment. A mean incidence of 1% was calculated, and there was a 0.0% to 5% range.

Caries

Thirteen of 1650 teeth evaluated in 13 studies^{53,55,57-65,68,69} developed carious lesions. There was a mean incidence of 0.8% and a range from 0.0% to 5%.

Periodontal disease

Periodontal health was assessed in 8 studies.^{48,53,55,57,63-65,68} Of the 942 crowns evaluated, any

Table IV. Most common resin-bonded prosthesis complications

	Number of prostheses studied/affected	Mean incidence
Debonding	7029/1481	21%
Tooth discoloration	343/62	18%
Caries	3426/242	7%
Porcelain fracture	1126/38	3%
Periodontal disease	748/0	0.0%

(no significant changes)

changes noted were either not significant or subjectively determined to be of no permanent detriment.

RESIN-BONDED PROSTHESES

Forty-eight studies⁷³⁻¹²⁰ present complications data regarding resin-bonded prostheses. There were 56 published studies but only 48 different patient groups, because there were multiple publications reporting on the same patients at different time intervals. The studies with the longer follow-up times were included in this article, and those presenting earlier data¹²¹⁻¹²⁸ were excluded from the mean complications calculations but included in relation to specific complications. In the 48 studies, a total of 1823 complications were reported in conjunction with 7029 prostheses for a mean complications incidence of 26%. The length of the studies ranged from 1 month to 15 years, with an average study length of about 4 years. In addition to the 48 patient groups, there were 5 studies¹²⁹⁻¹³³ that only evaluated the effect of resin bonded prostheses on the periodontium, 1 that assessed marginal fit,¹³⁴ a literature review¹³⁵ comparing the failure rates of resin-bonded prostheses with conventional fixed partial dentures and implant prostheses, and several articles¹³⁶⁻¹⁴¹ that assessed the survival of resin-bonded prostheses. In 1991, a meta-analysis¹⁴² was performed on available clinical studies.

Thirty-seven studies^{73-83,85-87,89-94,96-101,105,108,109,111-116,119,120} evaluated the prostheses for periods between 1 to 4 years and reported a mean complications incidence of 25% (1304 of 5204 prostheses affected). Eleven studies^{84,88,95,102-104,106,107,110,117,118} provided data about prosthesis complications after 5+ years and reported a mean complications incidence of 28% (519 of 1825 prostheses affected).

The following 5 factors were evaluated in a sufficient number of studies to be included in this article: debonding, abutment tooth discoloration, abutment tooth caries, porcelain fracture, and periodontal disease (Table IV). Three studies^{103,105,108} provided data related to all 5 complications, 4 articles^{79,80,83,106} reported on 4 of the 5 complications, 4 studies^{84,93,116,117} evaluated 3 of

the 5 complications, and 13 publications^{81,85,86,91,94,97-100,112,114,118,120} covered 2 of the 5 complications. Twenty-four^{73-78,82,87-90,92,95,96,101,102,104,107,109-111,113,115,119} of the 48 studies only reported on 1 of the 5 complications.

Debonding

Forty-eight studies⁷³⁻¹²⁰ evaluated the incidence of debonding. A total of 1481 of 7029 prostheses debonded (mean incidence of 21% with a range of 0.0% to 52%). The rate of debonding varied with the length of the clinical study. There were 11 studies with less than 2 years of postplacement evaluation^{73,77,78,81-83,85,87,89,97,105} and a mean debonding rate of 10%. Twenty-six studies^{74-76,79,80,86,90-94,96,98-101,108,109,111-116,119,120} ranged in length from 2 to 5 years with a mean debonding rate of 20%. A mean debonding rate of 24% was associated with the 11 studies^{84,88,95,102-104,106,107,110,117,118} evaluating prostheses for periods in excess of 5 years.

Debonding was evaluated in relationship to arch, arch location (anterior versus posterior), presence of abutment tooth preparation, gender, age, span length, and occlusal forces. These factors were assessed in a sufficient number of studies to be included in this article. Other factors (abutment mobility, trauma, bonding area) were evaluated but not in a sufficient number of studies (3 or more) to be reported.

Maxillary and mandibular debonding rates were compared in 27 studies. Six studies^{76,78,91,113,115,117} reported increased debonding in the maxilla, 8 studies^{77,90,93,98-100,109,116} found higher debonding in the mandible, and 13 studies^{79,84,86,87,95,103,104,106-108,111,112,118} found no significant difference between arches. No conclusive trend was noted.

Twenty-three studies compared anterior and posterior prostheses. Higher posterior debonding rates were reported in 8 studies,^{77,90,93,98,99,113,116,117} whereas higher anterior debond rates were found in 4 studies.^{82,91,96,123} No significant differences were reported in 11 studies.^{84,87,100,103,104,106-108,111,112,118} Again, no conclusive trend was observed.

A comparison was made between minimal/no abutment tooth preparation and a retentive tooth preparation in 9 studies. The retentive tooth preparations were not always illustrated but frequently were described as having 1 or more of the following features: proximal guiding surface, extended over a broad area of the teeth, proximal grooves, pinholes, and rests. Three studies^{86,109,118} reported no significant effect as the result of tooth preparation, whereas 5 studies^{84,101,106,107,124} reported substantial debonding rate decreases when the teeth were prepared. In these 5 studies, prostheses without retentive tooth preparations had a mean debonding rate of 47%, whereas those with retentively prepared abutments exhibited a mean debonding rate of 11%.

The effect of gender was evaluated in 8 studies. No significant difference was reported in 5 studies^{87,96,104,111,115}, whereas 3 studies^{79,98,103} reported a higher debonding rate in male patients. No conclusive trend was noted.

Four studies^{87,104,115,121} reported higher debonding rates in young patients, whereas 2 other studies^{96,103} found no significant difference. Two studies described "young" as being less than 20 years old, and another study indicated "young" as being less than 30 years old. A possible trend toward higher debonding rates with young patients was noted.

Six studies^{87,98,100,104,111,118} assessed the effect of span length by reporting data regarding prostheses longer than 3 units in length,^{87,118} prostheses with more than 1 pontic,^{100,104,111} or prostheses with more than 2 retainers.^{98,100,104} Three of the 6 studies^{86,99,103} provided debonding incidence percentages that permitted comparisons of short and longer span prostheses. Three of the studies reported the comparison as being either higher with prostheses over 3 units in length,¹¹⁸ 2 times the number of debondings with more than 2 retainers,⁹⁸ or debonding at an earlier time when there was more than 1 pontic.¹¹¹ The mean debonding incidence of short span prostheses was 25%. The longer span prostheses had a mean debonding rate of 52%.

Eight studies^{78,79,85,89,91,94,103,117,121} evaluated the effect of occlusal forces on the debonding rate. Two of these studies indicated that 70%¹²¹ and 45%⁸⁹ of the debonding was associated with prostheses placed in the presence of heavy occlusal forces. The other studies when combined indicated that 22% of the debondings (31 of 143 debondings) were attributable to heavy occlusal forces.

Abutment tooth discoloration

The presence of metal on the lingual surface produced discoloration of abutment teeth. This complication, the second most common, was reported in 7 studies.^{79-81,103,105,106,108} Five of the studies^{80,81,103,105,108} provided a percentage incidence, whereas 2 others^{79,106} reported its occurrence but did not indicate the number of prostheses affected by this complication. The 5 studies, when combined, indicate that 62 of 343 prostheses exhibited tooth discoloration for a mean incidence of 18% and a range of 3% to 37%.

Abutment tooth caries

Twenty-two studies^{79,80,83,84,86,93,94,98,100,103,105,106,108,109,112,114,116-118,121,122,134} reported on the occurrence of caries. The mean incidence of caries for the 22 studies was 7% (242 of 3426 prostheses affected by caries). A finding of no caries was reported in 9 studies.^{79,80,83,84,93,105,116,117,122} Six studies^{86,94,98,106,121,134} reported a caries incidence of less than 2%, and 7 stud-

ies^{100,103,108,109,112,114,118} reported an incidence greater than 2%. The incidence range was from 0.0% to 12%. Of the 13 studies reporting the presence of caries, seven^{86,98,100,106,108,109,112} reported the caries occurred in conjunction with debonded retainers, four^{94,103,114,118} did not indicate whether the retainer was bonded or debonded, and 2 studies^{121,130} stated the caries incidence was not associated with debonding.

Porcelain fracture

The presence of fractured porcelain was assessed in 15 studies.^{79-81,84,85,91,93,103,105,106,108,116,122,123,128} The mean incidence for the 15 studies was 3% (38 of 1126 prostheses experienced porcelain fracture). Four studies^{79,80,122,123} reported no fractures, and the 11 other studies^{81,84,85,91,93,103,105,106,108,116,128} reported incidences ranging from 0.8% to 8%.

Periodontal disease

The effect of the prosthesis on abutment tooth periodontal health was reported in 15 studies.⁸ Seven of the studies^{8,28,32,34,50,62,68} found no periodontal problems or no increased incidence of periodontal disease, and 4 reported the presence of mild inflammation.^{12,46,52,60} In 1 study,⁴⁹ there was 1 abutment tooth that was extracted after 4 years because of a progressive periodontal condition. Three studies reported statistically significant changes that were not considered to be clinically relevant by the authors of all 3 articles.^{37,59,61} Factors evaluated in these studies included plaque index, gingival index, pocket depth, attachment level, and gingival recession.

POSTS AND CORES

There are 12 clinical studies^{16,143-153} that report the total number of posts and cores evaluated and the total number of complications encountered. There were 279 complications found among the 2784 posts and cores in the 12 studies, producing a mean complications incidence of 10%. Among the 12 studies, observation times were as short as 1 year and as long as 25 years. The average study length was about 6 years. Additional studies^{33,154-161} have been published with clinical data about post and core complications, but they did not present the total number of complications encountered, or they only presented data regarding 1 or 2 types of complications. One study¹⁶² performed a meta-analysis of available studies, and 1 study¹⁶³ developed a mechanical longevity estimation model.

Three studies^{16,146,150} evaluated the posts and cores for periods between 1 to 4 years and recorded a mean complications incidence of 11%. One of the 3 studies¹⁴⁶ indicated the posts were observed over periods from 2 to 10 years. Because a mean observation time was not disclosed, a decision was made to include this data with the

Table V. Most common post and core complications

	Number of posts and cores studied/affected	Mean incidence
Post loosening	2596/135	5%
Root fracture	3043/95	3%
Caries	1047/16	2%
Periodontal disease	283/6	2%

1- to 4-year studies. Nine studies^{143-145,147-149,151-153} evaluated the posts over periods between 5 and 10 years, with a mean complications incidence of 10%. One study¹⁴⁵ evaluated posts over 1 to 25 years, and there also was no information about the average observation time. A decision was made to include this data in the group that included studies longer than 4 years.

The following 4 complications were evaluated in 3 or more studies and were therefore included in this article: post loosening, root fracture, caries, and periodontal disease (Table V). One study¹⁴⁴ presented data regarding all 4 of these complications, whereas 5 studies^{146-148,150,152} presented data for 3 of the 4 complications. Five studies^{16,145,151,155,161} covered 2 of the complications, and 2 studies^{154,158} reported on only 1 complication. The effect of the tooth position in the arch was assessed in 6 studies,^{147,151-153,159,161} but specific incidence numbers were not published, thereby preventing any calculations. Three of the 6 studies noted higher failure rates in the anterior maxilla,¹⁵¹⁻¹⁵³ and 2 studies^{147,161} indicated the position of the tooth in the arch was not a significant factor. Three other factors (root perforations,^{145,160} bent/fractured posts,^{146,152} and endodontic failures^{147,148}) were evaluated, but incidence data were only available in 2 studies. Therefore the data were not included.

Post loosening

Eleven studies^{16,144-148,150-152,155,161} provided numerical data related to post loosening. A total of 135 of 2596 posts loosened from the root for a mean incidence of 5% (range of 0% to 10%).

Root fracture

There were 13 studies^{16,144-148,150-152,154,155,158,161} with root fracture incidence data. Two studies^{154,158} only reported data related to root fractures and did not comment on other complications or the overall complications incidence. Ninety-five fractures were recorded in 3043 teeth, producing a mean incidence of 3% (range of 0% to 11%).

Caries

Four studies^{144,146,150,152} reported on the presence of caries. Of the 1047 posts and cores evaluated in the 4

studies, 16 were affected by caries. The mean incidence was 2% with a range from 0.8% to 9%.

Periodontal disease

Three studies^{144,147,148} identified the number of teeth restored with posts and cores that failed because of periodontal reasons. Six failures were recorded in the 283 teeth evaluated, producing a mean incidence of 2% (range from 1% to 3%).

SUMMARY

The complications information presented in this study identifies trends that can be effectively used to develop treatment plans that optimize success and to communicate appropriate expectations to patients. Conventional fixed partial dentures had the greatest complications incidence (27%), with resin bonded prostheses having a comparable incidence (26%). Single crowns (11%) and posts and cores (10%) had comparable complications incidences. All-ceramic crowns had the lowest incidence (8%) of complications.

The most common complications associated with conventional fixed partial dentures were caries (18% of abutments and 8% of prostheses), need for endodontic treatment (11% of abutments and 8% of prostheses), loss of retention (7% of prostheses), esthetics (6% of prostheses), periodontal disease (4% of prostheses), tooth fracture (3% of prostheses), and prosthesis/porcelain fracture (2% of prostheses). With resin bonded prostheses, the most common complications were debonding (21% of prostheses), tooth discoloration (18% of prostheses), caries (7% of prostheses), and porcelain fracture (3% of prostheses). The most common complications associated with conventional single crowns were need for endodontic treatment (3%), porcelain fracture (3%), loss of retention (2%), periodontal disease (0.6%), and caries (0.4%). The most common post and core complications were post loosening (5%), root fracture (3%), caries (2%), and periodontal disease (2%). With all-ceramic crowns, the most common complications were crown fracture (7%), loss of retention (2%), need for endodontic treatment (1%), and caries (0.8%).

REFERENCES

- Merriam Webster's Collegiate Dictionary. 10th ed. Springfield, MA: Merriam-Webster; 1993. p. 236.
- Hursey RJ. A clinical survey of the failure of crown and bridges. *South Carolina Dent J* 1958;16:4-11.
- Lundqvist P, Nilson H. A clinical re-examination of patients treated with pinledge-crowns. *J Oral Rehabil* 1982;9:373-87.
- Cheung GS. A preliminary investigation into the longevity and causes of failure of single unit extracoronal restorations. *J Dent* 1991;19:160-3.
- Palmqvist S, Swartz B. Artificial crowns and fixed partial dentures 18 to 23 years after placement. *Int J Prosthodont* 1993;6:279-85.
- Milleding P, Haag P, Neroth B, Renz I. Two years of clinical experience with Procera titanium crowns. *Int J Prosthodont* 1998;11:224-32.
- Walton TR. A 10-year longitudinal study of fixed prosthodontics: clinical characteristics and outcome of single-unit metal-ceramic crowns. *Int J Prosthodont* 1999;12:519-26.
- Bergman B, Bessing C, Ericson G, Lundquist P, Nilson H, Andersson M. A 2-year follow-up study of titanium crowns. *Acta Odontol Scand* 1990;48:113-7.
- Nilson H, Bergman B, Bessing C, Lundqvist P, Andersson M. Titanium copings veneered with Procera Ceramics: a longitudinal clinical study. *Int J Prosthodont* 1994;7:115-9.
- Jones JC. The success rate of anterior crowns. *Br Dent J* 1972;132:399-403.
- Coornaert J, Adriaens P, De Boever J. Long-term clinical study of porcelain-fused-to-gold restorations. *J Prosthet Dent* 1984;51:338-41.
- Meeuwissen R, Eschen S. Prosthodontic treatment and retreatment of 845 servicemen. *J Prosthet Dent* 1985;53:425-7.
- Leempoel PJ, Eschen S, De Haan AF, Van't Hof MA. An evaluation of crowns and bridges in a general dental practice. *J Oral Rehabil* 1985;12:515-28.
- Strub JR, Stiffler S, Scharer P. Causes of failure following oral rehabilitation: biological versus technical factors. *Quintessence Int* 1988;19:215-22.
- Black SM, Charlton G. Survival of crowns and bridges related to luting cements. *Restorative Dent* 1990;6:26-30.
- Schwartz NL, Whitsett LD, Berry TG, Stewart JL. Unserviceable crowns and fixed partial dentures: life-span and causes for loss of serviceability. *J Am Dent Assoc* 1970;81:1395-401.
- Walton JN, Gardner FM, Agar JR. A survey of crown and fixed partial denture failures: length of service and reasons for replacement. *J Prosthet Dent* 1986;56:416-21.
- Jackson CR, Skidmore AE, Rice RT. Pulpal evaluation of teeth restored with fixed prostheses. *J Prosthet Dent* 1992;67:323-5.
- Morrant GA. Bridges with particular relation to the periodontal tissues. *Dent Practit* 1956;6:178-86.
- Kantorowicz GF. Bridges an analysis of failures. *Dent Practit* 1968;18:176-8.
- Roberts DH. The failure of retainers in bridge prostheses. An analysis of 2000 retainers. *Br Dent J* 1970;128:117-24.
- Reuter JE, Brose MO. Failures in full crown retained dental bridges. *Br Dent J* 1984;157:61-3.
- Randow K, Glantz PO, Zoger B. Technical failures and some related clinical complications in extensive fixed prosthodontics. An epidemiological study of long-term clinical quality. *Acta Odontol Scand* 1986;44:241-55.
- Karlsson S. A clinical evaluation of fixed bridges, 10 years following insertion. *J Oral Rehabil* 1986;13:423-32.
- Karlsson S. Failures and length of service in fixed prosthodontics after long-term function. A longitudinal clinical study. *Swed Dent J* 1989;13:185-92.
- Carlson BR, Yontchev E, Carlsson GE. Extensive fixed partial dentures on mandibular canine teeth: a 5-year recall study. *Int J Prosthodont* 1989;2:265-71.
- Cheung GS, Dimmer A, Mellor R, Gale M. A clinical evaluation of conventional bridgework. *J Oral Rehabil* 1990;17:131-6.
- Ericson G, Nilson H, Bergman B. Cross-sectional study of patients fitted with fixed partial dentures with special reference to the caries situation. *Scand J Dent Res* 1990;98:8-16.
- Budtz-Jorgensen E, Isidor F. A 5-year longitudinal study of cantilevered fixed partial dentures compared with removable partial dentures in a geriatric population. *J Prosthet Dent* 1990;64:42-7.
- Laurell L, Lundgren D, Falk H, Hugoson A. Long-term prognosis of extensive polyunit cantilevered fixed partial dentures. *J Prosthet Dent* 1991;66:545-52.
- Valderhaug J. A 15-year clinical evaluation of fixed prosthodontics. *Acta Odontol Scand* 1991;49:35-40.
- Decock V, De Nayer K, De Boever JA, Dent M. 18-Year longitudinal study of cantilevered fixed restorations. *Int J Prosthodont* 1996;9:331-40.
- Sundh B, Odman P. A study of fixed prosthodontics performed at a university clinic 18 years after insertion. *Int J Prosthodont* 1997;10:513-9.
- Lindquist V, Karlsson S. Success rate and failures for fixed partial dentures after 20 years of service: Part I. *Int J Prosthodont* 1998;11:133-8.
- Hammerle CH, Ungerer MC, Fantoni PC, Bragger U, Burgin W, Lang NP. Long-term analysis of biologic and technical aspects of fixed partial dentures with cantilevers. *Int J Prosthodont* 2000;13:409-15.

36. Leempoel PJ, Kayser AF, Van Rossum GM, De Haan AF. The survival rate of bridges. A study of 1674 bridges in 40 Dutch general practices. *J Oral Rehabil* 1995;22:327-30.
37. Creugers NH, Kayser AF, van't Hof MA. A meta-analysis of durability data on conventional fixed bridges. *Community Dent Oral Epidemiol* 1994;22:448-52.
38. Scurria MS, Bader JD, Shugars DA. Meta-analysis of fixed partial denture survival: prostheses and abutments. *J Prosthet Dent* 1998;79:459-64.
39. Bergenholtz G, Nyman S. Endodontic complications following periodontal and prosthetic treatment of patients with advanced periodontal disease. *J Periodontol* 1984;55:63-8.
40. Glantz PO, Ryge G, Jendresen MD, Nilner K. Quality of extensive fixed prosthodontics after five years. *J Prosthet Dent* 1984;52:475-9.
41. Ödman PA, Karlsson S. Follow-up study of patients with bridge constructions performed by private dental surgeons and at a university clinic, 8 years following insertion. *J Oral Rehabil* 1988;15:55-63.
42. Foster LV. Failed conventional bridge work from general dental practice: clinical aspects and treatment needs of 142 cases. *Br Dent J* 1990;168:199-201.
43. Glantz PO, Nilner K, Jendresen M, Sundberg H. Quality of fixed prosthodontics after 15 years. *Acta Odontol Scand* 1993;51:247-52.
44. Valderhaug J, Jokstad A, Ambjorsen E, Norheim PW. Assessment of the periapical and clinical status of crowned teeth over 25 years. *J Dent* 1997;25:97-105.
45. Makila E, Salonen M. A follow-up study of partial crowns as bridge retainers. *Proc Finn Dent Soc* 1975;71:15-28.
46. Gustavsen F, Silness J. Clinical and radiographic observations after 6 years on bridge abutment teeth carrying pinledge retainers. *J Oral Rehabil* 1986;13:295-8.
47. Reichen-Graden S, Lang NP. Periodontal and pulpal conditions of abutment teeth. Status after four to eight years following the incorporation of fixed reconstructions. *Schweiz Monatsschr Zahnmed* 1989;99:1381-5 German.
48. Wolf JE, Hakala PE, Kolehmainen L, Jarvienen V. A follow-up study of porcelain and acrylic jacket crowns. *Proc Finn Dent Soc* 1978;74:54-8.
49. McLean JW. The Future for Dental Porcelain. In: McLean JW, editor. *Proceedings of the First International Symposium on Ceramics*. Chicago: Quintessence; 1983. p. 13-40.
50. Moffa JP, Lugassy AA, Ellison JA. Clinical evaluation of a castable ceramic material. Three year study. IADR abstract No. 43. *J Dent Res* 1988;67:118.
51. Richter E, Augthun M. [Dicor glass ceramic crowns]. *Dtsch Zahnärztl Z* 1989;44:785-7. German.
52. Erpenstein H, Kerschbaum T. [Fracture rate of Dicor crowns under clinical conditions]. *Dtsch Zahnärztl Z* 1991;46:124-8. German.
53. Nahara Y, Sadamori S, Hamada T. Clinical evaluation of castable apatite ceramic crowns. *J Prosthet Dent* 1991;66:754-8.
54. Hankinson JA, Cappetta EG. Five years' clinical experience with a leucite-reinforced porcelain crown system. *Int J Periodontics Restorative Dent* 1994;14:138-54.
55. Kelsey WP 3rd, Cavel T, Blankenau RJ, Barkmeier WW, Wilwerding TM, Latta MA. 4-year clinical study of castable ceramic crowns. *Am J Dent* 1995;8:259-62.
56. Scotti R, Catapano S, D'Elia A. A clinical evaluation of In-Ceram crowns. *Int J Prosthodont* 1995;8:320-3.
57. Pang SE. A report of anterior In-Ceram restorations. *Ann Acad Med Singapore* 1995;24:33-7.
58. Huls A. All-ceramic restorations with the In-Ceram system. 6 years of clinical experience. Bad Säckingen, Germany: VITA Zahnfabrik H. Rauter GmbH & co. KG; 1995. p. 1-31.
59. Probst L. Four year clinical study of glass-infiltrated, sintered alumina crowns. *J Oral Rehabil* 1996;23:147-51.
60. Fradeani M, Aquilano A. Clinical experience with Empress crowns. *Int J Prosthodont* 1997;10:241-7.
61. Lehner C, Studer S, Brodbeck U, Scharer P. Short-term results of IPS-Empress full-porcelain crowns. *J Prosthodont* 1997;6:20-30.
62. Oden A, Andersson M, Krystek-Ondracek I, Magnusson D. Five-year clinical evaluation of Procera AllCeram crowns. *J Prosthet Dent* 1998;80:450-6.
63. Burke FJ, Qualthrough AJ, Wilson NH. A retrospective evaluation of a series of dentin-bonded ceramic crowns. *Quintessence Int* 1998;29:103-6.
64. Sjogren G, Lantto R, Tillberg A. Clinical evaluation of all-ceramic crowns (Dicor) in general practice. *J Prosthet Dent* 1999;81:277-84.
65. Sjogren G, Lantto R, Granberg A, Sundstrom BO, Tillberg A. Clinical examination of leucite-reinforced glass-ceramic crowns (Empress) in general practice: a retrospective study. *Int J Prosthodont* 1999;12:122-8.
66. Malament KA, Socransky SS. Survival of Dicor glass-ceramic dental restorations over 14 years: Part I. Survival of Dicor complete coverage restorations and effect of internal surface acid etching, tooth position, gender, and age. *J Prosthet Dent* 1999;81:23-32.
67. Malament KA, Socransky SS. Survival of Dicor glass-ceramic dental restorations over 14 years. Part II: effect of thickness of Dicor material and design of tooth preparation. *J Prosthet Dent* 1999;81:662-7.
68. McLaren EA, White SN. Survival of In-Ceram crowns in a private practice: a prospective clinical trial. *J Prosthet Dent* 2000;83:216-22.
69. Haselton DR, Diaz-Arnold AM, Hillis SL. Clinical assessment of high-strength all-ceramic crowns. *J Prosthet Dent* 2000;83:396-401.
70. Malament KA, Grossman DG. Clinical application of bonded Dicor crowns: Two-year report. IADR abstract No. 1523. *J Dent Res* 1990;69:299.
71. Probst L. Survival rate of In-Ceram restorations. *Int J Prosthodont* 1993;6:259-63.
72. Kelsey WP III, Cavel WT, Blankenau J, Barkmeier WW, Wilwerding TM, Matranga LF. Two-year clinical study of castable ceramic crowns. *Quintessence Int* 1995;26:15-20.
73. Scheer B, Silverstone LM. Replacement of missing anterior teeth by etch retained bridges. *J Int Assoc Dent Child* 1975;6:17-9.
74. Kuhlke KL, Drennon DG. An alternative to the anterior single-tooth removable partial denture. *J Int Assoc Dent Child* 1977;8:11-5.
75. Denehy GE, Howe DF. A conservative approach to the missing anterior tooth. *Quintessence Int* 1979;10:23-9.
76. Jenkins CB. Etch-retained anterior pontics. A 4-year study. *Br Dent J* 1978;144:206-8.
77. Livaditis GJ. Resin-bonded cast restorations: clinical study. *Int J Periodontics Restorative Dent* 1981;1:70-9.
78. Shaw MJ, Tay WM. Clinical performance of resin-bonded cast metal bridges (Rochette bridges). A preliminary report. *Br Dent J* 1982;152:378-80.
79. Bergendal B, Hallonsten AL, Koch G, Ludvigsson N, Olgart K. Composite retained onlay bridges. *Swed Dent J* 1983;7:217-25.
80. Eshleman JR, Moon PC, Barnes RF. Clinical evaluation of cast metal resin-bonded anterior fixed partial dentures. *J Prosthet Dent* 1984;51:761-4.
81. LaBarre EE, Russell D. Update on resin-bonded bridges. *CDA Journal* 1984;12:108-11.
82. Hudgins JL, Moon PC, Knap FJ. Particle-roughened resin-bonded retainers. *J Prosthet Dent* 1985;53:471-6.
83. Chew CL. The acid-etched fixed partial denture: a two-year report. *J Prosthet Dent* 1985;54:173-5.
84. Behr M, Leibrock A, Stich W, Rammelsberg P, Rosentritt M, Handel G. Adhesive-fixed partial dentures in anterior and posterior areas. Results of an on-going prospective study begun in 1985. *Clin Oral Investig* 1998;2:31-5.
85. Creugers NH, van't Hof MA, Vrijhoef MM. A clinical comparison of three types of resin-retained cast metal prostheses. *J Prosthet Dent* 1986;56:297-300.
86. Kellett M. The etch-retained metal restoration in hospital clinical use. *Br Dent J* 1987;163:259-62.
87. Marinello CP, Kerschbaum T, Heinenberg B, Hinz R, Peters S, Pfeiffer P, et al. Experiences with resin-bonded bridges and splints—a retrospective study. *J Oral Rehabil* 1987;14:251-60.
88. Williams VD, Denehy GE, Thayer KE, Boyer DB. Resin bonded prostheses: A ten year retrospective study. IADR Abstract No. 739. *J Dent Res (special issue)* 1987;66:199.
89. Wiltshire WA, Ferreira MR, Nel JC. Clinical evaluation of resin-bonded bridges at 1-3 years. IADR Abstract No. 740. *J Dent Res (special issue)* 1987;66:199.
90. Mohl G, Mehra R, Ford A. Clinical evaluation of etched-metal resin-bonded fixed partial dentures. *J Prosthet Dent* 1988;59:403-4.
91. Clyde JS, Boyd T. The etched cast metal resin-bonded (Maryland) bridge: a clinical review. *J Dent* 1988;16:22-6.
92. Hickel R, Voss A. [Comparative studies on fissure sealing: composite versus Cermet cement]. *Dtsch Zahnärztl Z* 1989;44:59-62. German.
93. Al-Shammery AR, Saeed HI. A four-year clinical evaluation of acid etched bridges. *Saudi Dental J* 1989;1:56-9.

94. Ferrari M, Mason PN, Cagidiaco D, Cagidiaco MC. Clinical evaluation of resin bonded retainers. *Int J Periodontics Restorative Dent* 1989;9:207-19.
95. Creugers NH, Snoek PA, van't Hof MA, Kayser AF. Clinical performance of resin-bonded bridges: a 5-year prospective study. II. The influence of patient-dependent variables. *J Oral Rehabil* 1989;16:521-7.
96. Hussey DL, Pagni C, Linden GL. Performance of 400 adhesive bridges fitted in a restorative dentistry department. *J Dent* 1991;19:221-5.
97. Pröbster L, Setz J. Clinical performance of silane-coated, resin-bonded fixed partial dentures with two different preparational concepts. *Quintessence Int* 1990;21:707-12.
98. Olin PS, Hill EM, Donahue JL. Resin bonded bridges: University of Minnesota Recall Data. IADR Abstract No. 2031. *J Dent Res (Special issue)* 1990;69:362.
99. Crispin BJ. A longitudinal clinical study of bonded fixed partial dentures: the first 5 years. *J Prosthet Dent* 1991;66:336-42.
100. Chang HK, Zidan O, Lee IK, Gomez-Marin O. Resin-bonded fixed partial dentures: a recall study. *J Prosthet Dent* 1991;65:778-81.
101. Simon JF, Gartrell RG, Grogono A. Improved retention of acid-etched fixed partial dentures: a longitudinal study. *J Prosthet Dent* 1992;68:611-5.
102. Boyer DB, Williams VD, Thayer KE, Denehy GE, Diaz-Arnold AM. Analysis of debond rates of resin-bonded prostheses. *J Dent Res* 1993;72:1244-8.
103. Thayer KE, Williams VD, Diaz-Arnold AM, Boyer DB. Acid-etched, resin bonded cast metal prostheses: a retrospective study of 5- to 15-year-old restorations. *Int J Prosthodont* 1993;6:264-9.
104. Dunne SM, Millar BJ. A longitudinal study of the clinical performance of resin bonded bridges and splints. *Br Dent J* 1993;174:405-11.
105. Besimo C. Resin-bonded fixed partial denture technique: results of a medium-term clinical follow-up investigation. *J Prosthet Dent* 1993;69:144-8.
106. Barrack G, Bretz WA. A long-term prospective study of the etched-cast restoration. *Int J Prosthodont* 1993;6:428-34.
107. Rammelsberg P, Pospiech P, Gernet W. Clinical factors affecting adhesive fixed partial dentures: a 6-year study. *J Prosthet Dent* 1993;70:300-7.
108. Gilmour ASM, Ali A. Clinical performance of resin-retained fixed partial dentures bonded with a chemically active luting cement. *J Prosthet Dent* 1995;73:569-73.
109. Verzijden CW, Creugers NH, Mulder J. A multi-practice clinical study on posterior resin-bonded bridges: a 2.5 year interim report. *J Dent Res* 1994;73:529-35.
110. Samama Y. Fixed bonded prosthodontics: a 10-year follow-up report. Part I: Analytical overview. *Int J Periodontics Restorative Dent* 1995;15:424-35.
111. Mudassir A, Aboush YE, Hosein M, Hosein T, Padihar I. Long-term clinical performance of resin-bonded fixed partial dentures placed in a developing country. *J Prosthodont* 1995;4:233-6.
112. Priest G. An 11-year reevaluation of resin-bonded fixed partial dentures. *Int J Periodontics Restorative Dent* 1995;15:238-47.
113. Briggs P, Dunne S, Bishop K. The single unit, single retainer, cantilever resin-bonded bridge. *Br Dent J* 1996;181:373-9.
114. Kerschbaum T, Haastert B, Marinello CP. Risk of debonding in three-unit resin-bonded fixed partial dentures. *J Prosthet Dent* 1996;75:248-53.
115. Hussey DL, Linden GJ. The clinical performance of cantilevered resin-bonded bridgework. *J Dent* 1996;24:251-6.
116. Boening KW. Clinical performance of resin-bonded fixed partial dentures. *J Prosthet Dent* 1996;76:39-44.
117. Hansson O, Bergstrom B. A longitudinal study of resin-bonded prostheses. *J Prosthet Dent* 1996;76:132-9.
118. Pröbster B, Henrich GM. 11-year follow-up study of resin-bonded partial dentures. *Int J Prosthodont* 1997;10:259-68.
119. Besimo C, Gachter M, Jahn M, Hassell T. Clinical performance of resin-bonded fixed partial dentures and extracoronal attachments for removable prostheses. *J Prosthet Dent* 1997;78:465-71.
120. Botelho MG, Nor LC, Kwong HW, Kuen BS. Two-unit cantilevered resin-bonded fixed partial dentures—a retrospective, preliminary clinical investigation. *Int J Prosthodont* 2000;13:25-8.
121. Williams VD, Denehy GE, Thayer KE, Boyer DB. Acid-etch retained cast metal prostheses: a seven-year retrospective study. *J Am Dent Assoc* 1984;108:629-31.
122. Priest GF, Donatelli HA. A four-year clinical evaluation of resin-bonded fixed partial dentures. *J Prosthet Dent* 1988;59:542-6.
123. Hansson O, Moberg LE. Clinical evaluation of resin-bonded prostheses. *Int J Prosthodont* 1992;5:533-41.
124. De Kanter RJ, Creugers NH, Verzijden CW, Van't Hof MA. A five-year multi-practice clinical study on posterior resin-bonded bridges. *J Dent Res* 1998;77:609-14.
125. Mohl G, Mehra R. Clinical evaluation of etched metal resin bonded bridges. IADR Abstract No. 1278. *J Dent Res (special issue)* 1986;65:611.
126. Thompson VP, Wood M. Etched casting bonded retainer recalls: Results at 3-5 years. IADR Abstract No. 1282. *J Dent Res (special issue)* 1986;65:311.
127. Crispin BJ, Fisher DW, Avera S. Etched metal bonded restorations: Three years of clinical follow-up. IADR Abstract No. 1285. *J Dent Res* 1986;65 special issue:312.
128. Proebster L. Four-year clinical study of resin-bonded restorations utilizing the Silicoater technique. IADR Abstract No. 2036. *J Dent Res (special issue)* 1990;69:363.
129. Freilich MA, Niekraash CE, Katz RV, Simonsen RJ. The effects of resin-bonded and conventional fixed partial dentures on the periodontium: restoration type evaluated. *J Am Dent Assoc* 1990;121:265-9.
130. Wood M, Thompson VP, Romberg E, Morrison G. Resin-bonded fixed partial dentures. II. Clinical findings related to prosthodontic characteristics after approximately 10 years. *J Prosthet Dent* 1996;76:368-73.
131. Creugers NH, Snoek PA, Vogels AL. Overcontouring in resin-bonded prostheses: plaque accumulation and gingival health. *J Prosthet Dent* 1988;59:17-21.
132. Romberg E, Wood M, Thompson VP, Morrison GV, Suzuki JB. 10-year periodontal response to resin bonded bridges. *J Periodontol* 1995;66:973-7.
133. al-Wahadni A, Linder GJ, Hussey DL. Periodontal response to cantilevered and fixed-fixed resin bonded bridges. *Eur J Prosthodont Restor Dent* 1999;7:57-60.
134. Wood M, Kern M, Thompson VP, Romberg E. Ten-year clinical and microscopic evaluation of resin-bonded restorations. *Quintessence Int* 1996;27:803-7.
135. Priest GF. Failure rates of restorations for single-tooth replacement. *Int J Prosthodont* 1996;9:38-45.
136. Marinello CP, Kerschbaum T, Heinenberg B, Hinz R, Peters S, Pfeiffer P, et al. First experiences with resin-bonded bridges and splints—a cross-sectional retrospective study, Part II. *J Oral Rehabil* 1988;15:223-5.
137. Creugers NH, Kayser AF, Van't Hof MA. A seven-and-a-half-year survival study of resin-bonded bridges. *J Dent Res* 1992;71:1822-5.
138. Creugers NH, Kayser AF. An analysis of multiple failures of resin-bonded bridges. *J Dent* 1992;20:348-51.
139. Creugers NH, DeKanter RJ, van't Hof MA. Long-term survival data from a clinical trial on resin-bonded bridges. *J Dent* 1997;25:239-42.
140. Djemal S, Setchell D, King P, Wickens J. Long-term survival characteristics of 832 resin-retained bridges and splints provided in a post-graduate teaching hospital between 1978 and 1993. *J Oral Rehabil* 1999;26:302-20.
141. Smales RJ, Berekally TL, Webster DA. Predictions of resin-bonded bridge survivals, comparing two statistical models. *J Dent* 1993;21:147-9.
142. Creugers NH, Van't Hof MA. An analysis of clinical studies on resin-bonded bridges. *J Dent Res* 1991;70:146-9.
143. Roberts DH. The failure of retainers in bridge prostheses. An analysis of 2,000 retainers. *Br Dent J* 1970;128:117-24.
144. Wallerstedt D, Eliasson S, Sundstrom F. A follow-up study of screwpost-retained amalgam crowns. *Swed Dent J* 1984;8:165-70.
145. Sorensen JA, Martinoff JT. Clinically significant factors in dowel design. *J Prosthet Dent* 1984;52:28-35.
146. Linde LA. The use of composites as core material in root-filled teeth. II. Clinical investigation. *Swed Dent J* 1984;8:209-16.
147. Bergman B, Lundquist P, Sjogren U, Sundquist G. Restorative and endodontic results after treatment with cast posts and cores. *J Prosthet Dent* 1989;61:10-5.
148. Weine FS, Wax AH, Wenckus CS. Retrospective study of tapered, smooth post systems in place for 10 years or more. *J Endod* 1991;17:293-7.
149. Eckerbom M, Magnusson T, Martinsson T. Prevalence of apical periodontitis, crowned teeth and teeth with posts in a Swedish population. *Endod Dent Traumatol* 1991;7:214-20.
150. Hatzikyriakos AH, Reisis GI, Tsingos N. A 3-year postoperative clinical evaluation of posts and cores beneath existing crowns. *J Prosthet Dent* 1992;67:454-8.

151. Mentink AG, Meeuwissen R, Kayser AF, Mulder J. Survival rate and failure characteristics of all the metal post and core restoration. *J Oral Rehabil* 1993;20:455-61.

152. Torbjörner A, Karlsson S, Odman PA. Survival rate and failure characteristics for two post designs. *J Prosthet Dent* 1995;73:439-44.

153. Amakawa Y, Fukushima S, Tsubota Y. An 11-year clinical evaluation of posts and cores. IADR Abstract No. 933. *J Dent Res* (special issue) 1999;78:222.

154. Ross IF. Fracture susceptibility of endodontically treated teeth. *J Endod* 1980;6:560-5.

155. Turner CH. The utilization of roots to carry post-retained crowns. *J Oral Rehabil* 1982;9:193-202.

156. Turner CH. Post-retained crown failure: a survey. *Dent Update* 1982;9: 221, 224-6, 228-9.

157. Lewis R, Smith BG. A clinical survey of failed post retained crowns. *Br Dent J* 1988;165:95-7.

158. Morfis AS. Vertical root fractures. *Oral Surg Oral Med Oral Pathol* 1990;69:631-5.

159. Vire DE. Failure of endodontically treated teeth: classification and evaluation. *J Endod* 1991;17:338-42.

160. Grieve AR, McAndrew R. A radiographic study of post-retained crowns in patients attending a dental hospital. *Br Dent J* 1993;174:197-201.

161. Nanayakkara L, McDonald A, Setchell DJ. Restrospective analysis of factors affecting the longevity of post crowns. IADR Abstract No. 932. *J Dent Res* (special issue) 1999;78:222.

162. Creugers NH, Mentink AG, Kayser AF. An analysis of durability data on post and core restorations. *J Dent* 1993;21:281-4.

163. Huysmans MC, van der Varst PG. Mechanical longevity estimation model for post-and-core restorations. *Dent Mater* 1995;11:252-57.

Reprint requests to:
 DR CHARLES J. GOODACRE
 LOMA LINDA UNIVERSITY, SCHOOL OF DENTISTRY
 OFFICE OF THE DEAN
 LOMA LINDA, CA 92350
 FAX: 909-558-0483
 E-MAIL: cgoodacre@sd.llu.edu

Copyright © 2003 by The Editorial Council of *The Journal of Prosthetic Dentistry*.
 0022-3913/2003/\$30.00 + 0

doi:10.1016/S0022-3913(03)00214-2

Access to *The Journal of Prosthetic Dentistry* is reserved for print subscribers!

Full-text access to *The Journal of Prosthetic Dentistry Online* is available for all print subscribers. To activate your individual online subscription, please visit *The Journal of Prosthetic Dentistry Online*, point your browser to <http://www.mosby.com/prosdent>, follow the prompts to **activate online access here**, and follow the instructions. To activate your account, you will need your subscriber account number, which you can find on your mailing label (*note*: the number of digits in your subscriber account number varies from 6 to 10). See the example below in which the subscriber account number has been circled:

Sample mailing label

This is your subscription
 account number

*****3-DIGIT 001
SJ P1
FEB00 J010 C: 1 (1234567-890) U 05/00 Q: 1
J. H. DOE
531 MAIN ST
CENTER CITY, NY 10001-001

Personal subscriptions to *The Journal of Prosthetic Dentistry Online* are for individual use only and may not be transferred. Use of *The Journal of Prosthetic Dentistry Online* is subject to agreement to the terms and conditions as indicated online.